

Data Sheet

High Speed, Low Loss Multi-layer Materials

MEGTRON6

**Laminate R-5775
Prepreg R-5670**

Apr. 2021 No.21041931

Specification / Laminate R-5775

Property		Units	Test Method	Condition	Typical Value	
THERMAL	Glass Transition Temp (Tg)	C	DSC	As received	185	
			DMA	As received	210	
	Thermal Decomposition Temp (Td)		C	TGA	As received	410
	Time to Delam (T288)	Without Cu	Min	IPC TM-650 2.4.24.1	As received	> 120
		With Cu	Min	IPC TM-650 2.4.24.1	As received	> 120
	CTE : $\alpha 1$	X - axis	ppm / C	IPC TM-650 2.4.24	< Tg	14 - 16
		Y - axis	ppm / C	IPC TM-650 2.4.24	< Tg	14 - 16
		Z - axis	ppm / C	IPC TM-650 2.4.24	< Tg	45
CTE : $\alpha 2$	Z - axis	ppm / C	IPC TM-650 2.4.24	> Tg	260	
ELECTRICAL	Volume Resistivity		M Ω - cm	IPC TM-650 2.5.17.1	C-96/35/90	1 x 10 ⁹
	Surface Resistivity		M Ω	IPC TM-650 2.5.17.1	C-96/35/90	1 x 10 ⁸
	Dielectric Constant (Dk)	@ 1GHz	-	IPC TM-650 2.5.5.9	C-24/23/50	3.71
		@ 10GHz	-	IPC TM-650 2.5.5.5	C-24/23/50	3.61
	Dissipation Factor (Df)	@ 1GHz	-	IPC TM-650 2.5.5.9	C-24/23/50	0.002
		@ 10GHz	-	IPC TM-650 2.5.5.5	C-24/23/50	0.004
PHYSICAL	Water Absorption		%	IPC TM-650 2.6.2.1	D-24/23	0.14
	Peel Strength	1oz (H-VLP)	kN / m	IPC TM-650 2.4.8	As Received	0.8
	Flammability		-	UL	C-48/23/50	94V-0

Sample thickness ; 29.5 mil = 0.750 mm (Core Type 30)

* The data in the above table are not guaranteed values.

Specification / Laminate R-5775(K)

1GHz ; IPC TM650-2.5.5.9

2GHz-10GHz ; IPC TM650-2.5.5.5

Core Type	Actual Thickness		Cloth Style	ply	Typical Resin Content (%)	Typical Dk						Typical Df					
	mil	mm				1GHz	2GHz	4GHz	6GHz	8GHz	10GHz	1GHz	2GHz	4GHz	6GHz	8GHz	10GHz
2	2.0	0.050	1035	1	65	3.46	3.39	3.38	3.38	3.38	3.37	0.002	0.002	0.003	0.003	0.004	0.004
2.6	2.6	0.065	1080	1	57	3.65	3.58	3.57	3.56	3.56	3.55	0.002	0.002	0.003	0.003	0.004	0.004
2.6	2.6	0.065	1078	1	57	3.65	3.58	3.57	3.56	3.56	3.55	0.002	0.002	0.003	0.003	0.004	0.004
3	3.0	0.075	1078	1	63	3.49	3.42	3.41	3.40	3.40	3.39	0.002	0.002	0.003	0.003	0.004	0.004
3.5	3.5	0.090	1078	1	68	3.41	3.34	3.33	3.33	3.33	3.32	0.002	0.002	0.003	0.003	0.004	0.004
4	3.9	0.100	3313	1	54	3.71	3.64	3.63	3.63	3.62	3.61	0.002	0.002	0.003	0.003	0.004	0.004
4	3.9	0.100	1035	2	65	3.46	3.39	3.38	3.38	3.38	3.37	0.002	0.002	0.003	0.003	0.004	0.004
5	5.0	0.127	1078	2	57	3.65	3.58	3.57	3.56	3.56	3.55	0.002	0.002	0.003	0.003	0.004	0.004
5	4.9	0.125	2116	1	54	3.71	3.64	3.63	3.63	3.62	3.61	0.002	0.002	0.003	0.003	0.004	0.004
5	5.1	0.130	1080	2	57	3.65	3.58	3.57	3.56	3.56	3.55	0.002	0.002	0.003	0.003	0.004	0.004
6	5.7	0.146	1078	2	63	3.49	3.42	3.41	3.40	3.40	3.39	0.002	0.002	0.003	0.003	0.004	0.004
6	5.9	0.150	1080	2	63	3.49	3.42	3.41	3.40	3.40	3.39	0.002	0.002	0.003	0.003	0.004	0.004
7	7.0	0.178	1078	2	68	3.41	3.34	3.33	3.33	3.33	3.32	0.002	0.002	0.003	0.003	0.004	0.004
8	7.9	0.200	3313	2	54	3.71	3.64	3.63	3.63	3.62	3.61	0.002	0.002	0.003	0.003	0.004	0.004
10	9.8	0.250	2116	2	54	3.71	3.64	3.63	3.63	3.62	3.61	0.002	0.002	0.003	0.003	0.004	0.004
12	11.8	0.300	3313	3	54	3.71	3.64	3.63	3.63	3.62	3.61	0.002	0.002	0.003	0.003	0.004	0.004
16	15.7	0.400	3313	4	54	3.71	3.64	3.63	3.63	3.62	3.61	0.002	0.002	0.003	0.003	0.004	0.004
20	19.7	0.500	2116	4	54	3.71	3.64	3.63	3.63	3.62	3.61	0.002	0.002	0.003	0.003	0.004	0.004
25	24.6	0.625	2116	5	54	3.71	3.64	3.63	3.63	3.62	3.61	0.002	0.002	0.003	0.003	0.004	0.004
30	29.5	0.750	2116	6	54	3.71	3.64	3.63	3.63	3.62	3.61	0.002	0.002	0.003	0.003	0.004	0.004

* The data in the above table are not guaranteed values.

Specification / Prepreg R-5670(K)

1GHz ; IPC TM650-2.5.5.9 2GHz-10GHz ; IPC TM650-2.5.5.5

Cloth Style	Resin Content (%)	Typical Thickness (um)	Typical Dk						Typical Df					
			1GHz	2GHz	4GHz	6GHz	8GHz	10GHz	1GHz	2GHz	4GHz	6GHz	8GHz	10GHz
1027	75	49	3.28	3.21	3.20	3.20	3.20	3.19	0.002	0.002	0.003	0.003	0.004	0.004
1035	70	60	3.35	3.25	3.25	3.24	3.24	3.23	0.002	0.002	0.003	0.003	0.004	0.004
	73	68	3.29	3.22	3.22	3.21	3.21	3.20	0.002	0.002	0.003	0.003	0.004	0.004
	75	74	3.28	3.21	3.20	3.20	3.20	3.19	0.002	0.002	0.003	0.003	0.004	0.004
1080	64	76	3.47	3.40	3.39	3.39	3.39	3.38	0.002	0.002	0.003	0.003	0.004	0.004
	68	87	3.41	3.34	3.33	3.33	3.33	3.32	0.002	0.002	0.003	0.003	0.004	0.004
1078	64	77	3.47	3.40	3.39	3.39	3.39	3.38	0.002	0.002	0.003	0.003	0.004	0.004
	68	89	3.41	3.34	3.33	3.33	3.33	3.32	0.002	0.002	0.003	0.003	0.004	0.004
	72	104	3.31	3.24	3.23	3.23	3.23	3.22	0.002	0.002	0.003	0.003	0.004	0.004
	75	118	3.28	3.21	3.20	3.20	3.20	3.19	0.002	0.002	0.003	0.003	0.004	0.004
3313	54	98	3.71	3.64	3.63	3.63	3.62	3.61	0.002	0.002	0.003	0.003	0.004	0.004
	57	106	3.65	3.58	3.57	3.56	3.56	3.55	0.002	0.002	0.003	0.003	0.004	0.004
2116	54	125	3.71	3.64	3.63	3.63	3.62	3.61	0.002	0.002	0.003	0.003	0.004	0.004
	56	132	3.67	3.60	3.59	3.58	3.58	3.57	0.002	0.002	0.003	0.003	0.004	0.004

* The data in the above table are not guaranteed values.

Specification / Laminate R-5775(G)

1GHz ; IPC TM650-2.5.5.9

2GHz-10GHz ; IPC TM650-2.5.5.5

Core Type	Actual Thickness		Cloth Style	ply	Typical Resin Content (%)	Typical Dk						Typical Df					
	mil	mm				1GHz	2GHz	4GHz	6GHz	8GHz	10GHz	1GHz	2GHz	4GHz	6GHz	8GHz	10GHz
2	2.0	0.050	1035	1	65	3.46	3.39	3.38	3.38	3.38	3.37	0.002	0.002	0.003	0.003	0.004	0.004
2	2.0	0.050	1067	1	64	3.47	3.40	3.39	3.39	3.39	3.38	0.002	0.002	0.003	0.003	0.004	0.004
2.6	2.6	0.065	1080	1	57	3.65	3.58	3.57	3.56	3.56	3.55	0.002	0.002	0.003	0.003	0.004	0.004
2.6	2.6	0.065	1078	1	57	3.65	3.58	3.57	3.56	3.56	3.55	0.002	0.002	0.003	0.003	0.004	0.004
3	3.0	0.075	1078	1	63	3.49	3.42	3.41	3.40	3.40	3.39	0.002	0.002	0.003	0.003	0.004	0.004
3.5	3.5	0.090	1078	1	68	3.41	3.34	3.33	3.33	3.33	3.32	0.002	0.002	0.003	0.003	0.004	0.004
4	3.9	0.100	3313	1	54	3.71	3.64	3.63	3.63	3.62	3.61	0.002	0.002	0.003	0.003	0.004	0.004
4	3.9	0.100	1035	2	65	3.46	3.39	3.38	3.38	3.38	3.37	0.002	0.002	0.003	0.003	0.004	0.004
5	5.0	0.127	1078	2	57	3.65	3.58	3.57	3.56	3.56	3.55	0.002	0.002	0.003	0.003	0.004	0.004
5	4.9	0.125	2116	1	54	3.71	3.64	3.63	3.63	3.62	3.61	0.002	0.002	0.003	0.003	0.004	0.004
5	5.1	0.130	1080	2	57	3.65	3.58	3.57	3.56	3.56	3.55	0.002	0.002	0.003	0.003	0.004	0.004
6	5.7	0.146	1078	2	63	3.49	3.42	3.41	3.40	3.40	3.39	0.002	0.002	0.003	0.003	0.004	0.004
6	5.9	0.150	1080	2	63	3.49	3.42	3.41	3.40	3.40	3.39	0.002	0.002	0.003	0.003	0.004	0.004
7	7.0	0.178	1078	2	68	3.41	3.34	3.33	3.33	3.33	3.32	0.002	0.002	0.003	0.003	0.004	0.004
8	7.9	0.200	3313	2	54	3.71	3.64	3.63	3.63	3.62	3.61	0.002	0.002	0.003	0.003	0.004	0.004
10	9.8	0.250	2116	2	54	3.71	3.64	3.63	3.63	3.62	3.61	0.002	0.002	0.003	0.003	0.004	0.004
12	11.8	0.300	3313	3	54	3.71	3.64	3.63	3.63	3.62	3.61	0.002	0.002	0.003	0.003	0.004	0.004
16	15.7	0.400	3313	4	54	3.71	3.64	3.63	3.63	3.62	3.61	0.002	0.002	0.003	0.003	0.004	0.004
20	19.7	0.500	2116	4	54	3.71	3.64	3.63	3.63	3.62	3.61	0.002	0.002	0.003	0.003	0.004	0.004
22	21.9	0.555	7628	3	42	4.07	4.00	3.97	3.96	3.95	3.95	0.002	0.002	0.003	0.003	0.004	0.004
25	24.6	0.625	2116	5	54	3.71	3.64	3.63	3.63	3.62	3.61	0.002	0.002	0.003	0.003	0.004	0.004
29	29.1	0.740	7628	4	42	4.07	4.00	3.97	3.96	3.95	3.95	0.002	0.002	0.003	0.003	0.004	0.004
30	29.5	0.750	2116	6	54	3.71	3.64	3.63	3.63	3.62	3.61	0.002	0.002	0.003	0.003	0.004	0.004
37	36.4	0.925	7628	5	42	4.07	4.00	3.97	3.96	3.95	3.95	0.002	0.002	0.003	0.003	0.004	0.004

* The data in the above table are not guaranteed values.

Specification / Prepreg R-5670(G)

1GHz ; IPC TM650-2.5.5.9 2GHz-10GHz ; IPC TM650-2.5.5.5

Cloth Style	Resin Content (%)	Typical Thickness (um)	Typical Dk						Typical Df					
			1GHz	2GHz	4GHz	6GHz	8GHz	10GHz	1GHz	2GHz	4GHz	6GHz	8GHz	10GHz
1027	75	49	3.28	3.21	3.20	3.20	3.20	3.19	0.002	0.002	0.003	0.003	0.004	0.004
1035	70	60	3.35	3.25	3.25	3.24	3.24	3.23	0.002	0.002	0.003	0.003	0.004	0.004
	73	68	3.29	3.22	3.22	3.21	3.21	3.20	0.002	0.002	0.003	0.003	0.004	0.004
	75	74	3.28	3.21	3.20	3.20	3.20	3.19	0.002	0.002	0.003	0.003	0.004	0.004
1067	69	59	3.38	3.29	3.29	3.28	3.28	3.27	0.002	0.002	0.003	0.003	0.004	0.004
	72	67	3.31	3.24	3.23	3.23	3.23	3.22	0.002	0.002	0.003	0.003	0.004	0.004
	74	72	3.29	3.22	3.21	3.21	3.21	3.20	0.002	0.002	0.003	0.003	0.004	0.004
1080	64	76	3.47	3.40	3.39	3.39	3.39	3.38	0.002	0.002	0.003	0.003	0.004	0.004
	68	87	3.41	3.34	3.33	3.33	3.33	3.32	0.002	0.002	0.003	0.003	0.004	0.004
1078	64	77	3.47	3.40	3.39	3.39	3.39	3.38	0.002	0.002	0.003	0.003	0.004	0.004
	68	89	3.41	3.34	3.33	3.33	3.33	3.32	0.002	0.002	0.003	0.003	0.004	0.004
	72	104	3.31	3.24	3.23	3.23	3.23	3.22	0.002	0.002	0.003	0.003	0.004	0.004
	75	118	3.28	3.21	3.20	3.20	3.20	3.19	0.002	0.002	0.003	0.003	0.004	0.004
3313	54	98	3.71	3.64	3.63	3.63	3.62	3.61	0.002	0.002	0.003	0.003	0.004	0.004
	57	106	3.65	3.58	3.57	3.56	3.56	3.55	0.002	0.002	0.003	0.003	0.004	0.004
2116	54	125	3.71	3.64	3.63	3.63	3.62	3.61	0.002	0.002	0.003	0.003	0.004	0.004
	56	132	3.67	3.60	3.59	3.58	3.58	3.57	0.002	0.002	0.003	0.003	0.004	0.004

* The data in the above table are not guaranteed values.

++ Before purchase ++

【Notes before you use】

- Please verify the suitability and fitness for intended application by quality testing, evaluation or other means at your own option before any adoption, use or change of use conditions of a product listed in the datasheet.
- We would like to have a delivery specifications mutually agreed for the product that you have decided to use. The agreements defined in the delivery specifications are assigned higher priority.
- Please note that images shown may somewhat differ from the actual product in color.
- Please note that specifications and external design are subject to change for product improvement without notice.
- For details on products in the datasheet, please contact your distributor or our sales department.

【Safety Information】

- Before using the product, please read the delivery specifications carefully or contact the distributor from which you purchased the product or our sales department in order to use the product correctly.
- The products in the datasheet are Electronic circuit board materials for electronic and electrical devices. Please do not use them for other than specified use.

Please Contact us of more

【Technical Marketing】

- Japan (Osaka) TEL: 81-6-6904-2771
- USA (Mountain view) TEL: 1-408-861-3946
- Austria (Enns) TEL: 43-7223-883
- China (Guangzhou) TEL: 86-20-8713-0888

【Sales Offices】

- China (Hong Kong) TEL: 852-2529-3956
- China (Suzhou) TEL: 86-512-6825-1565
- China (Guangzhou) TEL: 86-20-8713-0888
- Korea (Seoul) TEL: 82-2-361-7873
- Taiwan (Hsinchu) TEL: 886-3-598-3201
- Thailand (Ayuthaya) TEL: 66-3533-0846
- Austria (Enns) TEL: 43-7223-883
- USA (Mountain view) TEL: 1-408-861-3946
- Japan (Osaka) TEL: 81-6-6904-2771

Panasonic Corporation
 Industrial Solutions Company
 Electronic Materials Business Division
 Circuit Board Materials Business Unit.
 Head Office: 1006 Kadoma, Kadoma City, Osaka 571-8506
 TEL: 81-6-6908-1101
industrial.panasonic.com/ww/electronic-materials